

Anti sulfatni agens

- Aditiv za malter
- *Forme (oblici) sa sulfatima ne rastvorivim u vodenim jedinjenjima*
- *Prevenција od oštećenja sulfatnim jedinjenjima*
- *Bezolovni*

OPIS PROIZVODA

Cementni, bezolovni prah, aditiv, koji se meša sa peskom i dodaje cementnom malteru.

OSOBINE

VANDEX ANTI SULPHATE reguje sa sulfatima, kako bi formiralo rastvorljivo jedinjenje koje štiti i sprečava sulfatne faze da prouzrokuju dalja pogoršanja.

PRIPREMA POVRŠINE

Ukloniti postojeći malter i malterisati do 1m iznad najvišeg stepena kontaminacije soli. Obiti sve betonske spojeve, osušiti sve površine i ukloniti sve postojeće mrlje.

Na mestima gde su prisutni nitrati, površina mora biti tretirana sa VANDEX MINERALIT pre primene VANDEX ANTI SULPHATE.

NAČIN MEŠANJA

VANDEX ANTI SULPHATE kao prah se direktno meša sa malterom koji se koristi za malterisanje u odnosu:

ANTI SULPHATE	Količina	
1.25 kg	25 kg (1 kanta)	VANDEX UNI MORTAR 1 Z
1.25 kg	25 kg	pesak/cement
6.00 kg	30 kg (1 kanta)	VANDEX ROUGH CAST

PRIMENA

Naneti cement pomešan sa VANDEX ANTI SULPHATE na prethodno pripremljenu površinu pri finom malterisanju ili kao podlogu bilo kojoj drugoj VANDEX hidroizolaciji.

Minimalna debljina nanetog sloja treba da bude 10 mm. Do zdrave površine, završni sloj mora biti zaštićen od brzog isušivanja.

Kako su sulfati vodopropusni, površine moraju biti dodatno zaštićene sa VANDEX BB 75 da bi se obezbedila potpuna zaštita površine.

POTROŠNJA MATERIJALA

Oko 1 kg/m² VANDEX ANTI SULPHATE na

- 10 mm VANDEX UNI MORTAR 1 Z ili pesak/cement malter.
- 5 mm VANDEX ROUGH CAST (kada se primenjuje na otvorenim površinama koje su pokrivene oko 50% .

PAKOVANJE

14 kg plastične, kante za (višenamensku upotrebu)

SKLADIŠTENJE

Kada se čuva na suvom mestu, u neotvorenom pakovanju, rok trajanja je do 12 meseci.

ZDRAVLJE I BEZBEDNOST

VANDEX ANTI SULPHATE sadrži cement. Izaziva iritaciju na koži. Rizik od oštećenja očiju. – Držati van domašaja dece. Ne udisati prašinu. Izbeci direktan kontakt sa očima ili kožom. U slučaju kontakta sa očima, isprati ih sa velikom količinom čiste vode i obratiti se lekaru. Obavezno je nošenje zaštitne obeće, rukavica i naočara.

Za detaljnije informacije posetiti veb sajt www.vandex.com.

TECHNICAL DATA	jedinica	opis
Agregatno stanje		Praškasta materija
Boja		Cement siva
Gustina tečne faze	kg/l	

All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained here is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee for success or failure, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



An RPM company

HEAD OFFICE AND INTERNATIONAL SALES :

VANDEX INTERNATIONAL LTD

P.O. Box · CH-4501 Solothurn/Switzerland

+41 32 626 36 36 · info@vandex.com · www.vandex.com

PRODUCTION :

VANDEX ISOLIERMITTEL -GESELLSCHAFT M.B.H.

P.O. Box · D -21487 Schwarzenbek/Germany

