

Elasticized waterproofing slurry

- **resistant to water aggressive for concrete**
- **suitable for areas of potential cracking**
- **applicable by mortar gun**

| | | |
|---|--|--|
| Permeability to CO ₂ Water vapour permeability Capillary water absorption Crack bridging ability Adhesion strength Reaction to fire Dangerous substances | $s_p > 50 \text{ m}$ class II 5 m $\leq s_p \leq 50 \text{ m}$ $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ A2 (20 °C) $\geq 0.8 \text{ MPa}$ class E complies with 5.3 | CE 0761 |
| | | Vandex Isoliermittel-GmbH Industriest. 19-23 DE-21493 Schwarzenbek 09 005/150 EN 1504-2:2004/ZA.1d,1e Surface protection coating |

PRODUCT DESCRIPTION

VANDEX CEMELAST is a two component polymer modified, cementitious surface treatment. It consists of VANDEX BB 75 (dry component) and VANDEX CEMELAST LIQUID (polymer component).

AREAS OF APPLICATION

- substrates: concrete and masonry
- waterproofing and protection against water and moisture
- for cracks and areas of potential cracking
- foundations, slabs, retaining walls, drinking water structures, etc.

PROPERTIES

Owing to its composition of cement, quartz with well graded aggregate and selected additives, as well as the admixture of the polymer component, a waterproof and elastic coating is achieved. The initial and final bonding ability of VANDEX CEMELAST is excellent, making it suitable to be applied on horizontal as well as vertical surfaces. It is durable, resistant to frost and heat after setting and at the same time vapour permeable. It is an active barrier to carbon dioxide (CO₂) and resistant to water aggressive for concrete. VANDEX CEMELAST is tested for use in contact with drinking water.

SURFACE PREPARATION

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance have to be removed by suitable means. – Water leaks must be stopped e.g. with VANDEX PLUG. – Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

Brick- and blockwork substrates

Any remaining plaster, render or other substances that could inhibit bonding must be removed back to the substrate. Gypsum, remains of wood or other foreign material must be removed by appropriate means. Loose pointing must be routed out and the substrate cleaned thoroughly.

MIXING

Before use, shake the container of the polymer component well. – Mix 25 kg of VANDEX BB 75 with 9 kg of VANDEX CEMELAST LIQUID in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a

high speed mechanical mixer. Where site conditions require, rinse the container with clean water and add it to the mixture.

APPLICATION

VANDEX CEMELAST is applied with trowel or suitable spray equipment.

Depending on the slurry consistency a maximum of 4 kg/m² can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to relevant specification.

If several coats are applied the previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat is textured by suitable means whilst still plastic to form a key.

Trowel application

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

Spray application

VANDEX CEMELAST can be applied with a suitable fine mortar spraying device. For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6 mm. The first layer of Vandex is applied in circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

Do not apply at temperatures below +5 °C, or to a frozen substrate.

CONSUMPTION

| Type of water impact | Recommended overall application rate | Number of layers |
|----------------------|--|------------------|
| Pressureless water | 2.5–3.5 kg/m ² | 1–2 |
| Water under pressure | 3.5–5.5 kg/m ² depending on water pressure | 2–3 |

Note:

Substrate and application conditions have to be observed. Depending on surface roughness, consumption may vary.



CURING

Provide suitable protection against extreme weather conditions (e.g. rain, sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 h. The VANDEX CEMELAST coating must be fully cured before getting in contact with water. Avoid formation of water films or condensation on top of coating during 7 days after application. Provide a relative humidity of 60–80% and good air exchange in enclosed areas.

| Temperature (°C): | Cure time (days): |
|-------------------|-------------------|
| 5–10 | 14 |
| 10–15 | 10 |
| 15–25 | 7 |
| 25–30 | 5 |

It is provided that the surface is thoroughly checked for hardness before filling. A careful cleaning and disinfection prior to the first operation is essential. Observe national laws and regulations.

BACKFILLING

Backfilling can be carried out 3 days after completion of the Vandex treatment. If there is a risk that the layer of Vandex will be damaged during back-filling (sharp-edged material) it must be protected by suitable means.

COATING

Surfaces treated with Vandex products which are to be coated or painted should be left to cure for at least 28 days. Coatings on top of a Vandex treatment have to be alkali resistant. Decorative coatings applied on the passive water pressure side are recommended to be water vapour permeable. When applying paint on an elasticized polymer modified product, it must have equivalent elastic properties.

FILLING OF WATER RETAINING STRUCTURES

Filling can take place when the surface treatment has hardened sufficiently, using the following guide referring to days after application:

PACKAGING

VANDEX BB 75: 25 kg PE-lined paper bag
VANDEX CEMELAST LIQUID: 9 kg PE-container

STORAGE

VANDEX BB 75: When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.
VANDEX CEMELAST LIQUID: Store in a frost-free place. Shelf life in unopened, undamaged original packaging is 8 months.

HEALTH AND SAFETY

Please refer to the actual Safety Data Sheets VANDEX BB 75 and VANDEX CEMELAST LIQUID on www.vandex.com.

| TECHNICAL DATA | | | |
|-----------------------------------|--------|---------------|--|
| | | Dry component | Polymer component |
| Appearance | | grey powder | milky white liquid |
| | | | |
| | | Wet mix | Hardened |
| Colour | | grey | grey VANDEX CEMELAST is not a decorative coating. |
| Density of wet mix | [kg/l] | approx. 1.65 | |
| Workability at 20 °C | [min.] | approx. 30 | |
| Setting time at 20 °C | [h] | | approx. 3–6 |
| Elongation at 20 °C | [%] | | approx. 13 |
| Tear resistance at 20 °C | [MPa] | | approx. 0.9 |
| Crack bridging capacity at +20 °C | [mm] | | ≤ 0.4 |
| Further data | | | refer to CE marking |

All data is averages of several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



HEAD OFFICE AND INTERNATIONAL SALES:

Vandex International Ltd

P.O. Box · CH-4501 Solothurn/Switzerland
+41 32 626 36 36 · info@vandex.com · www.vandex.com



PRODUCTION:

Vandex Isoliermittel-Gesellschaft m.b.H.

P.O. Box · D-21487 Schwarzenbek/Germany



ELASTIFIZIERTE DICHTUNGSSCHLÄMME

- **wasserdicht, geprüft bis 1,5 bar**
- **geeignet für rissgefährdete Zonen**
- **für Trinkwasser zugelassen**
- **schnelle Belastbarkeit**
- **beständig gegen betonaggressive Wässer**



PRODUKTBESCHREIBUNG

VANDEX CEMELAST ist eine zementgebundene, elastifizierte, 2-komponentige Dichtungsschlämme bestehend aus VANDEX BB 75 (Trockenkomponente) und VANDEX CEMELAST LIQUID (Anmach-flüssigkeit). VANDEX CEMELAST wird auf Beton, Mauerwerk und Putz zur Abdichtung gegen Wasser und Feuchtigkeit angewendet, in Kombination mit VANDEX KONSTRUBAND auch für Arbeitsfugen geeignet. VANDEX CEMELAST ist geeignet für rissgefährdete Zonen sowie für den Einsatz im Trinkwasserbereich.

Die Trockenkomponente besteht im Wesentlichen aus Zement, Quarz sowie chemischen Zusätzen. Durch Einmischen der Polymerkomponente entsteht nach dem Durchtrocknen eine wasserdichte, elastifizierte Schicht. Sie lässt sich auf horizontale und vertikale Flächen von Hand oder mittels eines Feinmörtelspritzgerät auftragen und ist nach der Verfestigung widerstandsfähig gegen wässrige Medien.

VERARBEITUNG




VANDEX CEMELAST
aufgetragen in 2 Schichten
mit Feinmörtelspritzgerät ...



... oder mit der Traufel

ANWENDUNG



VERBRAUCH

| Belastung | Empfohlene Gesamt-verbrauchsmenge in 2 Schichten | Gesamtschichtstärke (ca.) |
|-----------------------------------|---|----------------------------------|
| Nicht drückendes Wasser | 3,5 kg/m ² | 2,0 mm |
| Drückendes Wasser, Grundwasser | 5,5 kg/m ² | 3,0 mm |

TECHNISCHE DATEN

| | VANDEX CEMELAST (Frischmörtel) | VANDEX CEMELAST (ausgehärtet) |
|--|---|--|
| Farbe | grau | grau |
| Rohdichte des Frischmörtels | ca. 1,65 kg/l | – |
| Abbindezeit bei 20°C | ca. 3-6 Stunden | |
| Haftfestigkeit | – | ≥ 0,8 N/mm ² |
| Reissdehnung bei 20°C | – | ca. 13% |
| Rissüberbrückung 20°C | – | ≤ 0,4 mm |
| Weitere Daten | s. CE-Kennzeichnung auf dem technischen Merkblatt | |
| Alle Daten sind unter Laborbedingungen als Mittelwerte bestimmt worden. In der Praxis können die Vorbehandlungsart des Untergrundes, Einflüsse während der Applikation - z.B. Temperatur, Feuchtigkeit, Saugvermögen des Untergrundes - sowie die Nachbehandlungskonditionen diese Werte beeinflussen. | | |

Die hierin enthaltenen Informationen stützen sich auf unsere langjährigen Erfahrungen und beruhen auf unserem aktuellen Wissen. Wir können jedoch nur dann eine Gewährleistung übernehmen, wenn alle im speziellen Fall wirkenden Einflussfaktoren von uns vorab geprüft werden. Materialverbrauchsangaben sind Durchschnittswerte, die vor Ort variieren können.



HAUPTSITZ UND INTERNATIONALER VERKAUF: Vandex International Ltd

Postfach • CH-4501 Solothurn/Schweiz
+41 32 626 36 36 • info@vandex.com • www.vandex.com

PRODUKTION: Vandex Isoliermittel-Gesellschaft m.b.H.

Postfach 1406 • D-21487 Schwarzenbek/Deutschland

VERKAUF SCHWEIZ: Vandex AG

Postfach • CH-4501 Solothurn/Schweiz
+41 32 626 36 46 • info@vandex.ch • www.vandex.ch

VERKAUF DEUTSCHLAND/ÖSTERREICH: Vandex Isoliermittel-Gesellschaft m.b.H.

Postfach 1406 • D-21487 Schwarzenbek/Deutschland
+49 4151 89 15-0 • info@vandex.de • www.vandex.de

