

Vodoootporne PMMA membrane za otpadnu vodu

- Veoma fleksibilna i UV otporna
- Brza primena i sušenje
- Primjenljiva do -15 °C
- Odlična adheziona svojstva na različitim podlogama

OPIS PROIZVODA

PUMACRYL MEMBRANE je srednje viskozna, uretanski modifikovan PMMA membranski sistem na bazi metil metakrilata.

Dodavanjem PUMACRYL CATALYST, proces sušenja se inicira.

PODRUČJA PRIMENE

PUMACRYL MEMBRANE je tečna, lako primjenljiva, vodonepropusna membrana/premaz za horizontalne površine u sistemima otpadnih voda. Može se primeniti na betonu, metalu, na temperaturama između -15 °C do +30 °C.

Područja primene su raznovrsna, od novih objekata do reparacije starih i sređivanja dotrajalih.

SVOJSTVA

PUMACRYL MEMBRANE je jako fleksibilna membrane za popunjavanje pukotina, koja zadržava svoja svojstva i na temperaturama ispod -20 °C. Glavne osobine:

- Odlična svojstva na temperaturama nižim od -20 °C
- UV i otpornost na vrmeenske neprilike
- Vodonepropusna na pritisak vode
- Dobra hemijska otpornost (detaljnije informacije se daju po zahtevu klijenta)
- Otporna na udarce i habanje
- Odlična adheziona svojstva i mogućnost primene na raznim podlogama kao i temperaturama ispod 0 °C
- Jednostavna primena i brzo sušenje.
- Odlična kao material za među sloj, dobre hemijske osobine, lako se koriguje već urađen sloj
- Može se prepravljati, raditi preko nje ponovo

Na površini se ne smeju nalaziti tragovi slobodne vode. Površina mora biti čista, bez prašine, tragova masti i ulja. Ostaci materijala ili tragovi na površini mogu na primer biti uklonjeni peskarenjem dok se na primer tragovi masti i ulja mogu ukloniti plamenom. Pre primene PUMACRYL MEMBRANE, odgovarajući prajmer mora biti nanešen, uključujući peskarenje ako je potrebno.

MEŠANJE

Pre upotrebe, PUMACRYL MEMBRANE mora se pažljivo i temeljno mešati kako bi se postigla ravnomerna raspodela parfina po celoj zapremini proizvoda. PUMACRYL MEMBRANE THIX se zatim mesa sa katalizatorom PUMACRYL CATALYST (50% dibenzol peroksid).

Količina praha-katalizatora koji se dodaje zavisi od temperature:

Dodatak na 1 kg PUMACRYL MEMBRANE:

Temp.	%	Dodatak na 1 kg
30 °C	1	10 g PUMACRYL CATALYST
20 °C	1,3	13 g PUMACRYL CATALYST
10 °C	2,3	23 g PUMACRYL CATALYST
0 °C	4	40 g PUMACRYL CATALYST
-5 °C	4	40 g PUMACRYL CATALYST + 0,8 g PUMACRYL ACCELERATOR
-10 °C	4	40 g PUMACRYL CATALYST + 1,2 g PUMACRYL ACCELERATOR
-15 °C	4	40 g PUMACRYL CATALYST + 1,6 g PUMACRYL ACCELERATOR

težina/zapremina konverzije CATALYST:

$$\begin{aligned}1 \text{ cm}^3 &= 0,64 \text{ g} \\1 \text{ g} &= 1,57 \text{ cm}^3\end{aligned}$$

PRIMENA

PUMACRYL MEMBRANE se primjenjuje pomoću nazubljenog valjka

ČIŠĆENJE

Alati kojim se materijal nanosi moraju se očistiti odmah nakon upotrebe. Pomoću odgovarajućih detrdženata kao što su su etil acetat, aceton i metil metakrilat.

POTROŠNJA

Zavisi od područja primene.
Pogledati na Pumacryl specifikaciji.

PAKOVANJE

25 kg metalna kanta za višenamensku upotrebu

SKLADIŠTENJE

Kada se čuva na tamnom i suvom mjestu, u originalnom pakovanju, neotpakovan, rok upotrebe je 6 meseci. Idelni uslovi skladištenja su: 15–20 °C

BEZBEDNOST I ZDRAVLJE

Pogledati sigurnosni list na sajtu:
www.vandex.com.

Please note that an objective comparison with other data is only possible if norms and parameters are identical.

TEHNIČKI PODACI	Jedinica	Vrednost		Standard
Tečno stanje				
Viskozitet 25 °C	[mPa*s]	300-460		DIN 53018
Gustina, 25 °C	[g/ml]	1,36		ISO 2811
Vreme za primenu 20 °C	[min]	oko 15		
Vreme sušenja 20 °C	[min]	oko 60		
Temperatura sušenja	[°C]	+11,5		ISO 1516
Čvrsto stanje		na +23 °C	na -20 °C	
Boja	[RAL]	7040		
Obodna A tvrdoća	[IRHD]	95		NFP 98285
Obodna D tvrdoća		55		DIN 53505
Zatezna čvrstoća	[MPa]	7,4	7,8	ISO 527
Izduženje	[%]	340	310	ISO 527
Modul elastičnosti	[MPa]	88	615	ISO 527
Abrazija na 1000 ciklusa	[mg]	64		ISO 7784-2
Premoščavanje pukotina	[mm]	>5	>5	BPG

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.

Vandex®

An RPM Company

HEAD OFFICE AND INTERNATIONAL SALES:
Vandex International Ltd
P.O. Box · CH-4501 Solothurn/Switzerland
+41 32 626 36 36 · info@vandex.com · www.vandex.com

PRODUCTION :
Vandex Isoliermittel-Gesellschaft m.b.H.
P.O. Box · D-21487 Schwarzenbek/Germany


CERTIFIED MANAGEMENT SYSTEM
SCS
ISO 9001 / ISO 14001


CERTIFIED
MANAGEMENT SYSTEM
ENet