

### Cementno vodonepropusno jedinjenje za reparaciju

- Zaustavlja tekuću vodu
- Brzo deluje
- Trajan – postojan

#### OPIS PROIZVODA

Cementno, brzo delujuće jedinjenje za zaustavljanje vode i vlage, unapred spremno za upotrebu.

#### PODRUČJA PRIMENE

VANDEX PLUG se može koristiti kao unutrašnji ili spoljašnji vodootporni reparacioni malter ili kao brzo delujući malter kojim se postiže povećanje čvrstoće i elastičnosti materijala:

- Zaustavljanje curenja i prodiranja vode
- Zaptivanje pukotina koje propuštaju vodu
- Zaptivanje mokrih površina
- Zaptivanje pukotina u cevima-glinene,betonske
- Zaptivanje zglobovnih veza kod tunela
- Popravka delova u kojim je potrebno trenutno delovanje – zaustavljanje vode
- Kod ugradnje čeličnih elemenata u beton ili zid (železnične stanice)
- Kod betonskih – malterisanih elemenata pogođenih kišom
- Kod premazivanja kanala u kojima dolazi do konstantnog slijanja vode
- Podvodnih elemenata (sa dozvoljenim pristupom)

VANDEX PLUG se može koristiti na sledećim podlogama:

- beton
- zidani elemenati
- glinene površine
- kamen

#### OSOBINE

VANDEX PLUG ima sledeća fizička svojstva:

- Zaustavlja protok vode
- Deluje posle 30 sekundi nakon nanošenja
- Trajan-postojan
- Može se koristiti na podvodnim elementima
- Može se mešati sa vodom ili koristiti u suvom obliku
- Laka primena
- Pakovan tako da se može više puta koristiti

#### PRIPREMA POVRŠINE

Podloga mora biti čista, i bez bilo kakve kontaminacije. Pukotine moraju biti očišćene i jasno naglašene sa jasno definisanim prostorom koji se popunjava VANDEX PLUG.

#### NAČIN MEŠANJA

Vreme potrebno za delovanje materijala najčešće zavisi od količine korišćene vode za mešanje. Standard je (na 20 °C): 1 kg VANDEX PLUG sa oko 0,25 litara vode. VANDEX PLUG se mora dodati u vodu i brzo mešati. Vreme mešanja je 15 sekundi. Posle mešanja potrebno je iskoristiti u roku od 30 sekundi.

Tokom hladnijih dana koristiti mlaku vodu.

#### NANOŠENJE

Da bi se izbeglo preterano trošenje, mešati ga u malim količinama.

- Posle mešanja, iskorisitit VANDEX PLUG odmah na željenoj površini. Smesu pažljivo i ravnomerno naneti na površinu a zatim držati čvrsto 30 sekundi (koristiti gumene rukavice).
- Održavati površinu bez delovanja pritiska dok materijal ne počne da deluje.
- Ukloniti višak materijala.
- Pre nego što se tretirana površina dovede u kontakt sa vlagom, upotrebiti neki od uobičajnih VANDEX hidroizolacionih premaza.

U određenim okolnostima VANDEX PLUG se može upotrebiti i kao suvi prah.

Naneti na površinu i držati 30 do 40 sekundi.

#### POTROŠNJA

U zavisnosti od pukotine kroz koju prodire voda, otprilike po 0,3 kg VANDEX PLUG po jednoj pukotini.

#### PAKOVANJE

- 15 kg plastična kanta, (pogodna za više upotreba)
- 5 kg plastična kanta, (pogodna za više upotreba)

#### SKLADIŠTENJE

Može se skladištit do 12 meseci na suvim i tamnim mestima, ne oštećen i ne otvaran.

#### HEALTH AND SAFETY

Pogledati bezbednosni list na veb stranici [www.vandex.com](http://www.vandex.com).



TEHNIČKI PODACI	jedinica	
Izgled materijala		Praškasta supstanca
Boja		Siva
Gustina, na 25 °C	[kg/l]	oko 1,2
Komponentni sastav		Jednokomponentni
Temperaturna područja primene	[°C]	+5 do +25 °C
(Dozvoljeno kombinovanje temperature vode i temperature podloge)		
Vreme potrebno za delovanje	[sec]	oko 30 (posle mešanja)

All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a success full outcome, all circumstances in a individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



An RPM Company

#### HEAD OFFICE AND INTERNATIONAL SALES:

Vandex International Ltd

P.O. Box · CH-4501 Solothurn/Switzerland

+41 32 626 36 36 · info@vandex.com · www.vandex.com



#### PRODUCTION :

Vandex Isoliermittel-Gesellschaft m.b.H.

P.O. Box · D-21487 Schwarzenbek/Germany

